

Description:

The PD-2014 Reemay product is a spunbonded polyester fabric at approximately 1.0 oz/yd² (34 gsm).

Uses:

PD-2014 Reemay is designed for reinforcement of the Pli-Dek Hot Rubber (HR) Waterproofing System; hot applied rubber waterproofing membrane. The PD-2014 Reemay is an inter ply reinforcement used over the entire substrate area to form the Pli-Dek Hot Rubber (HR) Waterproofing System. The PD-2014 Reemay can also be used as reinforcement over cracks, construction joints and changes in plane.

Advantages:

- Excellent elongation
- Bridges hairline cracks, fills pin holes
- Non-Water absorptive
- Excellent low temperature flexibility

Color:

White

Package Size:

Roll size is 39 inches in width and 600 foot in length.

Storage:

Transport and store in original, unopened, undamaged containers. Protect from freezing. Do not store container in direct sunlight.

Technical Information:**Sheet Grab Tensile:**

(MD)22.3 (99)lb.

(XD)16.6 (74)lb.

(ASTM D 4632)

Sheet Trapezoid Tear:

(MD)6.2 (27.6)lb.

(XD)21.7 (97)lb.

(ASTM D 117)

Unit Weight1.0 (34) oz/yd

(ASTM D 3776)

TexTest Air Permeability.....886 (450) cfm

(ASTM D 737)

Thickness.....9.6 (0.24) mil

(ASTM D 1777)

Limitations:

PD-2014 Reemay is not intended for installation at drains, expansion joints or exposed flashing.

Clean-Up:

Wash with warm water and soap.

Technical Assistance:

Please contact Pli-Dek Systems, Inc. for any technical assistance you may need.

Disclaimer:

This information is furnished without warranty, representation, inducement or license of any kind, except sources believed by Pli-Dek Systems, Inc. to be accurate. Pli-Dek Systems, Inc. does not assume any legal responsibility for use or reliance on the information supplied here.

