

## PRODUCT INFORMATION SHEET GS88-1 ACCENT BASE SEALER

### Description:

The GS88-1 Accent Base Sealer is a premium quality elastomeric acrylic coating, which is a blend of high solid acrylic polymers that provides an elastomeric water repellent coating.

### Uses:

- Pli-Dek System
- Con-Dek System
- PD Texture Coat

### Advantages:

- Water Based
- Easy Clean-up
- Performs very well in hot and cold climates
- UV Resistant
- Excellent Hide and Color Retention
- Chemical Resistant
- Alkali and Moisture Resistant
- Custom Colors Available

### Color/Packaging:

GS88-1 Accent Base is available in Pli-Dek's 12 standard colors in a Low Sheen Finish. GS88-1 Accent Base is packaged in a 5-gallon pail.

### Storage:

Transport and store in original, unopened, undamaged containers. Protect from freezing. Do not store container in direct sunlight.

### Clean Up:

Clean tools and hands with warm soapy water and rinse thoroughly.

### Application Instructions:

#### Surface Preparation:

The surface must be clean, free of dirt, oil, and all foreign matter. Do not apply over mildew.

#### Application:

Box and mix all containers to ensure consistent coloring throughout. Cut in all edges with a brush and roll the entire surface with a ¾" inch nap roller. Roller must be suitable for paints and coating. Be sure to roll out GS88-1 Accent Base Sealer evenly, rolling in both directions. It is best to apply out of the direct sunlight and below 25°C (85°F). In some cases, 2 coats may be required.

#### Maintenance:

To remove dirt and mild stains use soap and a mild detergent (such as TSP), water, and a brush. For reseal requirements, please refer to the Pli-Dek Warranty. Please refer to Pli-Dek Maintenance Requirements for complete details.

### Cure Time:

Allow 4 hours between coats. Allow 8 hours before light foot traffic and 24 hours before normal foot traffic. Allow 48 hours before placing heavy objects on the surface.

### Coverage Rate:

Coverage rate is 100 square feet per gallon when applied with a ¾" nap roller (two coats may be necessary). Coverage may vary due to surface texture.

### Technical Data:

Solid Content	47-50% by weight 33-36% by volume
Elongation (ASTM D412-87)	225% (70°F) 150% (32°F)
Flexibility (ASTM D1737)	0°C ½" Mandrel Pass
Viscosity (KU) (ASTM D562-81)	95-100 (KU)
Water Vapor Transmission (ASTM E96-84)	Perms 7.5
VOC Content (ASTM D3960-90)	156 grams per liter
Tensile Strength (ASTM D412-87)	475 psi (70°F)
Flash Point (ASTM D56-87)	200°F
Freeze Thaw Resistance	50+ Cycles - Pass

### Warranty:

Please contact Pli-Dek, LLC. for details.

### Disclaimer:

*\*This information is furnished without warranty, representation, inducement or license of any kind, except sources believed by Pli-Dek LLC to be accurate. Pli-Dek LLC does not assume any legal responsibility for use or reliance on the information supplied here.*

### Technical Assistance:

Contact Pli-Dek LLC for any job specific questions.



Scan here to visit the Pli-Dek website